



C-1, 91/6, Phase I, B/h. Bank of India, G.I.D.C., Vatva, Ahmedabad - 382 445. (India) Phone : +91-79-3292 0774, 6450 1424 Fax : +91-79-25893014

TECHNICAL DATA SHEET

Name of Product	:	VIBASOL RED VHS (SOLVENT RED 135)
Class	:	Perione
Hue	:	Red

Vibfast Solvent Red 135 is a Red dyestuff anthraquinone dyestuff with excellent light fastness and very high thermal stability. It is soluble in most aromatic hydrocarbons, ketones and esters.

Fastness Properties:

Polymer	Concentration	Light Fastness
PS	Transparent 0.05% dye	7
ABS	Opaque, 0.01% dye + 1% TiO ₂	6
Thermal Stability	300° C (for 10 Min in PS)	

Applications:	Specifications	Typical Metal contents PPM
Vibfast Solvent Red 135 is recommended for the	Molecular Weight: 200	Zn, As, Cu, Se, Mg, Co, Sb: <0.01
coloration of the following	Lambda Max: 502.7 <u>+</u> 1 nm	Hg, Cd, Cr, Pb: < 1.00
resins:	M.P.: 318° C	Fe: <1.0
1. ABS	Moisture: 0.2%	
2. Polystyrene	Filter insoluble: 0.1% max	
3. Polycrarbonate	Particle Size: <100 mesh	
4. Acrylic		
5. SAN		
6. PMMA		

Packing: 10,20 & 25Kgs in Bags with 2 Plastic Liners. Transport Regulations: Non Hazardous Storage: For 5 Years, if properly stored Handling: subject to recommended handling.

Technical information, data and indications concerning function and application of the products are to be considered empirical values. Although the information is believed to be accurate, there is no warranty by Vibfast. None of the recommendations becomes part of the contractual or warranted quality of the products. Due to the fact that the conditions of individual use are beyond Vibfast's Control. Vibfast disclaims all responsibilities in connection with the use of the aforesaid material and does not warrant against any loss by reason of the supplied products.