




**Pigments for
Waterbase
Flexo Inks**



**vibfast
pigments
pvt.ltd.**



VIBFAST BLUE PIGMENT BLUE 1

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.30	≤45	7-8	200	5	5	5

VIBFAST BLUE 7160-160 PIGMENT BLUE 15:0

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.30	≤45	7-8	200	5	5	5



VIBFAST BLUE 7060-160 PIGMENT BLUE 15:1

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.30	≤45	7-8	280	5	5	5

VIBFAST BLUE D 2160 PIGMENT BLUE 15:3

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.30	≤45	7-8	280	5	5	5

VIBFAST BLUE - PIGMENT BLUE 1



VIBFAST BLUE 7160-160 - PIGMENT BLUE 15:0



VIBFAST BLUE 7060-160 - PIGMENT BLUE 15:1



VIBFAST BLUE D 2160 - PIGMENT BLUE 15:3



VIBFAST BLUE D 2180 PIGMENT BLUE 15:4

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.40	≤42	7-8	280	5	5	5

VIBFAST GREEN D 4001-162 PIGMENT GREEN 7

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.60	≤35	7-8	280	5	5	5

VIBFAST GREEN 4002 PIGMENT GREEN 36

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
5-6	1.45	≤25	5-6	200	5	5	3

VIBFAST VIOLET 4060 PIGMENT VIOLET 3

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	2.10	≤50	5-6	160	4	5	4

VIBFAST BLUE D 2180 - PIGMENT BLUE 15:4



VIBFAST GREEN D 4001-162 - PIGMENT GREEN 7



VIBFAST GREEN 4002 - PIGMENT GREEN 36



VIBFAST VIOLET 4060 - PIGMENT VIOLET 3





VIBFAST QUINACRIDONE VIOLET 4061 PIGMENT VIOLET 19

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
7-8	1.50	≤55	7-8	260	5	5	5

VIBFAST CARBAZOL VIOLET 4062 PIGMENT VIOLET 23

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
7-8	1.50	≤50	7-8	280	5	5	5


VIBFAST VIOLET 4063 PIGMENT VIOLET 27

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	2.10	≤25	4-5	160	4	5	5


VIBFAST YELLOW 4002 PIGMENT YELLOW 1

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.25	≤45	6-7	180	4-5	4-5	4-5

VIBFAST QUINACRIDONE VIOLET 4061 - PIGMENT VIOLET 19




VIBFAST CARBAZOL VIOLET 4062 - PIGMENT VIOLET 23



VIBFAST VIOLET 4063 - PIGMENT VIOLET 27



VIBFAST YELLOW 4002 - PIGMENT YELLOW 1





VIBFAST YELLOW 4003 PIGMENT YELLOW 3

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.55	≤45	6-7	180	4-5	4-5	4-5

VIBFAST YELLOW 4004 PIGMENT YELLOW 12

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.30	≤45	4-5	200	5	4-5	4

VIBFAST YELLOW 4005 PIGMENT YELLOW 13



Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.30	≤45	5-6	220	5	5	5

VIBFAST YELLOW 4006 PIGMENT YELLOW 14



Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.15	≤55	5-6	200	5	5	5

VIBFAST YELLOW 4003 - PIGMENT YELLOW 3

40% Loading MASS TONE 1/1



1/10 TINT TONE 1/20




VIBFAST YELLOW 4004 - PIGMENT YELLOW 12

40% Loading MASS TONE 1/1





1/10 TINT TONE 1/20





VIBFAST YELLOW 4005 - PIGMENT YELLOW 13

40% Loading MASS TONE 1/1





1/10 TINT TONE 1/20





VIBFAST YELLOW 4006 - PIGMENT YELLOW 14

40% Loading MASS TONE 1/1



1/10 TINT TONE 1/20





VIBFAST YELLOW 4007 PIGMENT YELLOW 17

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.30	≤55	6-7	200	5	4	5

VIBFAST YELLOW 4008 PIGMENT YELLOW 74

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.30	≤45	6-7	200	5	5	5

VIBFAST ISOINDOLINONE YELLOW 4200 PIGMENT YELLOW 139



Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.75	≤55	7-8	260	4	5	4

VIBFAST BEZIMIDAZOLONE YELLOW 4201 PIGMENT YELLOW 151


Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
7-8	1.50	≤50	7-8	260-280	5	5	4

VIBFAST YELLOW 4007 - PIGMENT YELLOW 17

40% Loading MASS TONE 1/1





1/10 TINT TONE 1/20





VIBFAST YELLOW 4008 - PIGMENT YELLOW 74

40% Loading MASS TONE 1/1




1/10 TINT TONE 1/20




VIBFAST ISOINDOLINONE YELLOW 4200 - PIGMENT YELLOW 139

40% Loading MASS TONE 1/1





1/10 TINT TONE 1/20



VIBFAST BEZIMIDAZOLONE YELLOW 4201 - PIGMENT YELLOW 151

40% Loading MASS TONE 1/1



1/10 TINT TONE 1/20



**VIBFAST YELLOW 4009
PIGMENT YELLOW 83**

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.30	≤55	5-6	220	5	5	5

**VIBFAST ORANGE 4050
PIGMENT ORANGE 5**

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.60	≤40	5-6	220	4	4-5	4-5

**VIBFAST ORANGE 4051
PIGMENT ORANGE 13**

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.40	≤50	4-5	240	4-5	4-5	4-5




**VIBFAST ORANGE 4052
PIGMENT ORANGE 34**

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.20	≤50	5-6	200	5	4	4

VIBFAST YELLOW 4009 - PIGMENT YELLOW 83

40% Loading **MASS TONE** 1/1



1/10 **TINT TONE** 1/20



VIBFAST ORANGE 4050 - PIGMENT ORANGE 5

40% Loading **MASS TONE** 1/1





1/10 **TINT TONE** 1/20



VIBFAST ORANGE 4051 - PIGMENT ORANGE 13

40% Loading **MASS TONE** 1/1


1/10 **TINT TONE** 1/20



VIBFAST ORANGE 4052 - PIGMENT ORANGE 34

40% Loading **MASS TONE** 1/1

1/10 **TINT TONE** 1/20





VIBFAST RED 4025 PIGMENT RED 2

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.30	≤50	5-6	200	5	4	4

VIBFAST RED 4027 PIGMENT RED 4

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.20	≤50	5-6	200	5	4	4



VIBFAST RED 4043 PIGMENT RED 22

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.20	≤40	6-7	180	4	3	3

VIBFAST RED 4041 PIGMENT RED 23

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.30	≤55	5-6	150	4	2	2

VIBFAST RED 4025 - PIGMENT RED 2



VIBFAST RED 4027 - PIGMENT RED 4



VIBFAST RED 4043 - PIGMENT RED 22



VIBFAST RED 4041 - PIGMENT RED 23



VIBFAST RED 4028:1 PIGMENT RED 48:1

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	2.00	≤50	5-6	220	5	4	4-5

VIBFAST RED 4028:3 PIGMENT RED 48:3

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.60	≤55	5-6	240	5	3	3


VIBFAST RED 4037:1 PIGMENT RED 49:1

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.60	≤50	4	200	2	3	3



VIBFAST RED 4030:1 PIGMENT RED 53:1

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.70	≤50	4	240	5	3	3

VIBFAST RED 4028:1 - PIGMENT RED 48:1



VIBFAST RED 4028:3 - PIGMENT RED 48:3



VIBFAST RED 4037:1 - PIGMENT RED 49:1



VIBFAST RED 4030:1 - PIGMENT RED 53:1





VIBFAST RED 4031 PIGMENT RED 57:1

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	0.70	≤65	4-5	230	5	5	4-5

VIBFAST QUINACRIDONE RED 4040 PIGMENT RED 122

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
7-8	1.45	≤50	7-8	280	5	5	5

VIBFAST RED 4033 PIGMENT RED 146

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.45	≤50	5-6	220	5	4-5	5

VIBFAST RED 4034 PIGMENT RED 170

Physical Data			Fastness Properties				
pH Value	Density	Oil Absorption	Light Fastness	Heat Resistance	Water Resistance	Acid Resistance	Alkali Resistance
6-7	1.30	≤50	6-7	240	5	5	5

VIBFAST RED 4031 - PIGMENT RED 57:1



VIBFAST QUINACRIDONE RED 4040 - PIGMENT RED 122



VIBFAST RED 4033 - PIGMENT RED 146



VIBFAST RED 4034 - PIGMENT RED 170





(AN ISO 9001, 14001 & 18001 CERTIFIED COMPANY)

MANUFACTURERS AND EXPORTERS OF PIGMENTS

**Corporate Office : "PALLADIUM", B1/801-806, 8th Floor, B/h. Divya Bhaskar Press,
Nr. Vodafone House, Corporate Road, Prahladnagar, Ahmedabad - 380 015. Gujarat, INDIA.**

Phone : +91 - 79 - 2970 5063, +91 - 90990 57223 / 24 • Fax : +91 - 79 - 2970 5064

E-mail : amit@vibfast.com • Website : www.vibfast.com