



VIBFAST PIGMENTS PVT LTD.,



C-1, 91/6, Phase 1, G.I.D.C., B/h. Bank of India,
 Vatva, Ahmedabad-382 445, INDIA
 Phone : 0091-79-32920774, 0091-79-64501424 Fax : 0091-79-25893014

E-Mail : amit@vibfast.com
 amit@vibgyorchemtex.com
 Website : www.vibgyorchemtex.com / www.vibfast.com

SPECIFICATION OF VIBFAST LAKE AMARANTH

Classification: -

1)	C.I. NO.	16185:1
2)	C.I.	Pigment Red -193
3)	CAS NO.	915-67-3 (Parent Colour)
4)	EINECS NO.	212-022-2 (Parent Colour)

Specification: -

No.	Characteristic	Limits		
1)	Shade			
	Description			
4)	Total Dye content on AS IS Basis	11 - 20%	21 – 30%	31 – 42%
5)	Total Dye Content on Dry Basis	11 - 20%	21 – 30%	31 – 42%
6)	Moisture at 110°C for 2 Hours	18% Max	18% Max	18% Max
7)	PH of 2% slurry	3.7 – 5.0	3.7 – 5.0	3.7 – 5.0
8)	Bleeding for Free Dye Content	0.4% Max	0.4% Max	0.4% Max
9)	Sieve Analysis by 325 mesh	85% Min	85% Min	85% Min
10)	Bulk density (g./ml)	0.4% Max	0.4% Max	0.4% Max
11)	Lead, mg/kg, Max.	10 Max	10 Max	10 Max
12)	Arsenic, mg/kg, Max.	3 Max	3 Max	3 Max
13)	Heavy metals mg/kg, max.	20 Max	20 Max	20 Max
14)	Mercury mg./kg	1 Max	1 Max	1 Max
15)	Cadmium mg./kg	1 Max	1 Max	1 Max

Dye content of $\pm 1\%$ is consistently maintained in Alluminium Lake Pigments from 11% to 42% strength